

# HM035NJ

Post Consumer Recycled High Density Polyethylene Resin

**Special Characteristics :** HM035NJ is recycled high density polyethylene injection molding grade with grayish-green color pellets appearance . This grade is used for variety injection molding applications of household product. Recycled plastic source is from post-consumer recycle HDPE food and beverage caps from domestic waste.

**Typical Applications :** Household, Crates, Pallets, Others

**Typical Properties :**

Properties	HM035NJ	Unit	Test Method
<b>Physical Properties</b>			
Melt Flow Rate (2.16 kg/190°C)	2.0	g/10 min	ASTM D1238
Density	0.957	g/cm <sup>3</sup>	ASTM D1505

<b>Mechanical Properties (Compression specimens)</b>			
Tensile Strength at Yield	270	kg/cm <sup>2</sup>	ASTM D638
Tensile Strength at Break	140	kg/cm <sup>2</sup>	ASTM D638
Elongation at Break	200	%	ASTM D638
Flexural Modulus	12,600	kg/cm <sup>2</sup>	ASTM D790
Notched Izod Impact Strength	4 (C)*	kg.cm/cm	ASTM D256

\*C = Complete Break

**Recommendation :**

Injection molding temperature : 170 - 220 °C

**Disclaimer:** To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however, we do not assume any liability what so ever for the accuracy and completeness of such information. We make no warranties which extend beyond the description contained herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of our products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

**Note :** Properties reported here are typical values of the product, not to be considered as specifications.

GC makes no representations as to the accuracy or completeness of the information contained herein.