

HM035NB

Post Consumer Recycled High Density Polyethylene Resin

Special Characteristics : HM035NB is purple color recycled high density polyethylene blow molding grade. They are used for wide variety blow molding applications of small to medium size container for detergent and personal care containers. Recycled plastic source is from post-consumer recycle bottle, which is collected from domestic waste only.

Typical Applications : Personal care containers, Detergent containers, Lubricant oil containers

Typical Properties :

Properties	HM035NB	Unit	Test Method
------------	---------	------	-------------

Physical Properties

Melt Flow Rate (2.16 kg/190°C)	0.58	g/10 min	ASTM D1238
Density	0.959	g/cm ³	ASTM D1505

Mechanical Properties (Based on compression specimens)

Tensile Strength at Yield	270	kg/cm ²	ASTM D638
Tensile Strength at Break	160	kg/cm ²	ASTM D638
Elongation at Break	330	%	ASTM D638
Flexural Modulus	12,600	kg/cm ²	ASTM D790
Notched Izod Impact Strength	6	kg.cm/cm	ASTM D256

Recommendation:

Extruder temperature : 165 -190 °C

Die temperature : 180 - 195 °C

Disclaimer: To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however, we do not assume any liability what so ever for the accuracy and completeness of such information. We make no warranties which extend beyond the description contained herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of our products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

Note : Properties reported here are typical values of the product, not to be considered as specifications.
GC makes no representations as to the accuracy or completeness of the information contained herein.