

TN085FB

Post Consumer Recycled Polyethylene Terephthalate Resin

Special Characteristics : TN085FB is recycled polyethylene terephthalate which is a post-consumer material. They are used for both sheet and bottle applications. Recycled plastic source is from unpigmented post-consumer recycle PET food and beverage bottle from domestic waste only.

Typical Applications : CSD Bottle food applications.

Typical Properties :

Properties	TN085FB	Unit	Test Method
Physical Properties			
Intrinsic Viscosity (IV)	0.85±0.03	dl/g	Relative to ASTM D4603
Acetaldehyde (AA)	Max 1.5	ppm	ENV-Method
Moisture Content	Max 0.2	%	ENV-Method
Color Properties			
L*	Min 70	-	CIELAB
b*	Max 1	-	CIELAB

Recommendation:

Barrel Temperature : 270 - 295 °C

Drying : 160 - 170 °C, 4 - 6 hrs.

FDA Statement :

Complies with Food and Drug Administration US FDA 21 CFR 177.1630, Commission Regulation (EU) 10/2011 and Thai-FDA under MOPH Notification No. 435 B.E. 2565 (2022) both process assessment and product testing.

Disclaimer: To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however, we do not assume any liability what so ever for the accuracy and completeness of such information. We make no warranties which extend beyond the description contained herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of our products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

Note : Properties reported here are typical values of the product, not to be considered as specifications.
GC makes no representations as to the accuracy or completeness of the information contained herein.